## 



TECAWORK<sup>®</sup> BD 148 - 275/300 g/m<sup>2</sup>

#### MAXIMUM COMFORT

This 100% cotton fabric feels naturally soft and ensures great wearers' comfort with its excellent breathability and moisture absorption.

#### INDUSTRIAL LAUNDERABLE

Well-suited for extensive industrial laundering.

### DURABLE

Engineered to design quality workwear.



made for life

# **TECAWORK®**

TECHNICAL DATA	TECAWORK®	TEST METHOD	
Quality	BD 148		
Width	152 cm (+2/-1 cm)	ISO 22198: 2006	
Weight	275/300 g/m <sup>2</sup> (±5%)	ISO 3801: 1978	
Composition	100% cotton	ISO 1833: 2020	
Construction	3/1 twill s	ISO 3572: 1976	
Available finishes	Sanforized		
Physical performance			
Tensile strength	1100 N x 650 N (±10%)	ISO 13934-1: 2013	
Tear strength	25 N x 25 N (±10%)	NEN-EN-ISO 13937-1: 2000	
Dimensional change	Max. ± 5 %	ISO 5077: 2007 After 5x cleaning cycles at 75 °C ISO 15797: 2018	
Care labelling			
Domestic laundering	$\overrightarrow{\mathbf{w}}$ $\overleftarrow{\mathbf{w}}$ $\overrightarrow{\mathbf{w}}$ $\overrightarrow{\mathbf{w}}$ $\overrightarrow{\mathbf{e}}$	NEN-EN-ISO 6330, 6N 60 °C: 2013	
Industrial laundering	75 °C - ISO 15797 White: Colour:	Visit our website for the laundering recommendations www.tencatefabrics.com Qualification label - ISO 30023	

CERTIFICATION		
	Öko-tex 100, class II	Centexbell; 1803034

COLOURS				
Bianco	Dimgray	Darkness	Deepsky	Indigo
00001	37094	57538	37097	47004



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.