## TECAWORK®



TECAWORK® BG 1003 – 255 g/m<sup>2</sup>

#### MAXIMUM COMFORT

This cotton-rich fabric feels naturally soft and ensures great wearers' comfort with its excellent breathability and moisture absorption.

### INDUSTRIAL LAUNDERABLE

Engineered to retain its looks even after hightemperature industrial laundering – minimizing the cost of ownership.

### STRONG AND DURABLE

Truly fitted for hard-working environments thanks to its strength and greater abrasion resistance features, which will allow a longer garment life cycle.



made for life

# **TECAWORK®**

TECHNICAL DATA	TECAWORK®	TEST METHOD
Quality	BG 1003	
Width	153 cm (+2/-1 cm)	ISO 22198: 2006
Weight	255 g/m² (±5%)	ISO 3801: 1978
Composition	65/35% polyester/cotton	ISO 1833: 2020
Construction	2/1 twill	ISO 3572: 1976
Available finishes	Easy-Care	
Physical performance		
Tensile strength	1000 N x 500 N (±10%)	ISO 13934-1: 2013
Tear strength	40 N x 30 N (±10%)	NEN-EN-ISO 13937-1: 2000
Dimensional change	Max.±3%	ISO 5077: 2007 After 5x cleaning cycles at 75 °C ISO 15797: 2018
Care labelling		
Domestic laundering	$\overrightarrow{\text{of}}$ $$ $$ $$ $$ $\overrightarrow{P}$	NEN-EN-ISO 6330, 6N 60 °C: 2013
Industrial laundering	75 °C - ISO 15797 White: Colour:	Visit our website for the laundering recommendations www.tencatefabrics.com Qualification label - ISO 30023

CERTIFICATION			
	Öko-tex 100, class II	Centexbell; 1803034	

HV Yellow	Papaya	River	Navy	Granite	Mole Grey	Black
64516	61070	60662	63805	64126	61094	60475



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.