


TECAWORK®



**ANY WORK,
ANYWHERE**

TECAWORK®
KG 308 – 245 g/m²

STRONG AND DURABLE

Truly fitted for hard-working environments thanks to its strength and greater abrasion resistance features, which will allow a longer garment life cycle.

INDUSTRIAL LAUNDERABLE

Engineered to retain its looks even after high-temperature industrial laundering – minimizing the cost of ownership.

COMFORTABLE

This fabric is a great fit for workwear that combines comfort and ultimate performance.

TECHNICAL DATA	TECAWORK®	TEST METHOD
Quality	KG 308	
Width	153 cm (+2/-1 cm)	ISO 22198: 2006
Weight	245 g/m ² (±5%)	ISO 3801: 1978
Composition	65/35% polyester/cotton	ISO 1833: 2020
Construction	2/1 twill	ISO 3572: 1976
Available finishes	Standard: Easy Care, Optional: Hydro-Tec	

Physical performance		
Tensile strength	1500 N x 900 N (±10%)	ISO 13934-1: 2013
Tear strength	50 N x 40 N (±10%)	
Dimensional change	Max. ± 3 %	ISO 5077: 2007 After 5x cleaning cycles at 75 °C ISO 15797: 2018

Care labelling		
Domestic laundering		NEN-EN-ISO 6330, 6N 60 °C: 2013
Industrial laundering	75 °C - ISO 15797 White: Colour:	Visit our website for the laundering recommendations www.tencatefabrics.com Qualification label - ISO 30023

CERTIFICATION		
	High-Visibility colour	ISO EN 20471: 2013
	Food-Hygiene - workwear in food business	DIN 10524-2012-04
	Öko-tex 100, class II	Centexbell; 1803034

COLOURS							
HV Yellow 62016	Buttercup 60366	Marmelade 66777	Papaya 65293	China 62705	F.E. Red 61086	Pilot 66748	Rhino 62894
Royal Box 60624	Sailor Blue 61088	Deep Blue 61076	Navy 63805	Mood Indigo 66213	Dublin 66907	Bottle Green 61090	Everglade 65522
Spruce Green 60830	Safari 66783	Bianco 00001	Winter 60944	Steel 62893	Mole Grey 61094	Charcoal 60380	Black 60475
Black Night 64958							

Ten Cate Protect B.V.
is certified according:



Member of:



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.