

TECAWORK®



**ANY WORK,
ANYWHERE**

TECAWORK®
KG 46 – 205 g/m²

STRONG AND DURABLE

Truly fitted for hard-working environments thanks to its strength and greater abrasion resistance features, which will allow a longer garment life cycle.

INDUSTRIAL LAUNDERABLE

Engineered to retain its looks even after high-temperature industrial laundering – minimizing the cost of ownership.

COMFORTABLE

This fabric is a great fit for workwear that combines comfort and ultimate performance.

TECHNICAL DATA	TECAWORK®	TEST METHOD
Quality	KG 46	
Width	153 cm (+2/-1 cm)	ISO 22198: 2006
Weight	205 g/m ² (±5%)	ISO 3801: 1977
Composition	50/50% polyester/cotton	ISO 1833: 2020
Construction	2/1 twill	ISO 3572: 1976
Available finishes	Easy-Care	

Physical performance		
Tensile strength	1000 N x 750 N (±10%)	ISO 13934-1: 2013
Tear strength	30 N x 30 N (±10%)	NEN-EN-ISO 13937-1: 2000
Dimensional change	Max. ±2.5%	ISO 5077: 2007 After 5x cleaning cycles at 75 °C ISO 15797: 2018

Care labelling		
Domestic laundering		NEN-EN-ISO 6330, 6N 60 °C: 2013
Industrial laundering	75 °C - ISO 15797 White: Colour:	Visit our website for the laundrying recommendations www.tencatefabrics.com Qualification label - ISO 30023

CERTIFICATION		
	OEKO-TEX® STANDARD 100, class II	Centexbel; 1803034

COLOURS				
Bianco 00001	Sky 60563	Caribe 62719	Surgeon 62110	The colours shown are standard options available with a minimum order of 100 meters. This service program is subject to change. Please scan the QR code or visit our website for the latest overview of standard colours.



For any additional colours or specific colour combination requirements beyond this service, please contact your TenCate Protective Fabrics representative.

Ten Cate Protect B.V. is certified according:



Member of E.T.S.A



Product certification:



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.