

TECAWORK®



**ANY WORK,
ANYWHERE**

TECAWORK®
KG 46 – 205 g/m²

STRONG AND DURABLE

Truly fitted for hard-working environments thanks to its strength and greater abrasion resistance features, which will allow a longer garment life cycle.

INDUSTRIAL LAUNDERABLE

Engineered to retain its looks even after high-temperature industrial laundering – minimizing the cost of ownership.

COMFORTABLE

This fabric is a great fit for workwear that combines comfort and ultimate performance.

TECAWORK®

| TECHNICAL DATA | TECAWORK® | TEST METHOD |
|--------------------|----------------------------|-----------------|
| Quality | KG 46 | |
| Width | 153 cm (+2/-1 cm) | ISO 22198: 2006 |
| Weight | 205 g/m ² (±5%) | ISO 3801: 1978 |
| Composition | 50/50% polyester/cotton | ISO 1833: 2020 |
| Construction | 2/1 twill | ISO 3572: 1976 |
| Available finishes | Easy-Care | |

| Physical performance | | |
|----------------------|-----------------------|--|
| Tensile strength | 1000 N x 750 N (±10%) | ISO 13934-1: 2013 |
| Tear strength | 30 N x 30 N (±10%) | NEN-EN-ISO 13937-1: 2000 |
| Dimensional change | Max. ±2.5% | ISO 5077: 2007 After 5x cleaning cycles at 75 °C ISO 15797: 2018 |

| Care labelling | | |
|-----------------------|--------------------------------------|--|
| Domestic laundering | | NEN-EN-ISO 6330, 6N 60 °C: 2013 |
| Industrial laundering | 75 °C - ISO 15797 White: Colour: | Visit our website for the laundrying recommendations www.tencatefabrics.com Qualification label - ISO 30023 |

| CERTIFICATION | | |
|---------------|-----------------------|---------------------|
| | Öko-tex 100, class II | Centexbell; 1803034 |

| COLOURS | | | | |
|-------------------|--------------|-----------------|------------------|-----------------|
| Burgundy 60732 | Sky 60563 | Caribe 62719 | Surgeon 62110 | Bianco 00001 |

Ten Cate Protect B.V.
is certified according:



Member of:



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics Europe declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.