ARAMID



Omniweave[™]750

MADE FOR THERMAL RISKS

This aramid fabric's time-tested construction offers wearers reliable inherent FR protection against heat and flame.

DURABILITY AND STRENGTH

Tough enough for rugged environments, our aramid fabrics stand up to the uniquely dangerous environments professionals face on the job.

TRUSTED LEGACY

A time-tested solution, industrial professionals around the globe have put their trust in the performance of aramid fabrics for over 50 years.



ARAMID

TECHNICAL DATA*		OMNIWEAVE™750		
Nominal Weight			7.5 osy (254 gsm)	
Construction			Woven	
Color			Royal, Spruce, Black, Dark Navy and F.S. Navy	
Fiber Content			Aramid, Anti-Stat	
Certification			ASTM 1506, NFPA 1975, NFPA 1977, NFPA 2112, CGSB 155.20, ISO 11612	
Flame Resistance				
Manikin Burn CGSB 155.20, NFPA 2112	Predicted Body Burn		Pass	
Thermal Protective Performance NFPA 70E, ASTM 1959	ATPV Rating		6.9 cal/cm ²	
	PPE Category		Category 1	
Vertical Flame	After flame		< 2.0 sec	
ASTM 6413, NFPA 2112	Char length		< 4.0 in (100 mm)	
Thermal Shrinkage NFPA 2112	Initial and 3x After	Wash	< 10%	
Physical Testing				
Tensile Strength ASTM D5034 (Warp x Fill)	Initial		285 x 274 lbf (1,270 x 1,220 N)	
Elmendorf Tear ASTM D1424, (Wrap x Fill)			12.6 x 11.5 lbf (56 x 51 N)	
Dimensional Stability AATCC 135			< 3.0%	
Seam Stability ASTM D434, Fource at 0.25 in slippage			40 lbf (179 N)	
Appearance Score 5 (best) to 1 (Worst)				
Color Fastness	Laundering AATCC 612A	Shade Change	Up to 4*	
	Laundering AATCC 613A	Shade Change	Up to 3*	
	Crocking AATCC 8	Wet	Up to 4.5*	
		Dry	Up to 5*	

^{*} Appearance is dependent on shade of fabric.

AVAILABLE COLORS					OPTIONAL COLORS
Royal	Spruce	Black	Dark Navy	FS Navy	Additional color options may be available. Please contact TenCate Protective Fabrics for more information. Color shades and textures may vary. Please contact your sales representative for swatch samples.

After 20 Hours

After 40 Hours

After 60 Hours

Initial: 60 min





Xenon Light

Pilling Resistance ASTM D3512

Exposure AATCC 16



Up to 4*

Up to 3*

Up to 5*

Up to 3-4*



All mentioned data must be considered as indicative values. To the best of our knowledge all information contained herein is accurate. TenCate Protective Fabrics declines any form of liability related to the use of the attached specimen that shall be regarded as a sample only and therefore not meant to be used in any form of garment making.